

CLAIMS

1. A paint composition for leather, comprising a fluorine-containing resin and a silicone oil.

5

2. A paint composition for leather, comprising a curable fluorine-containing resin, a curing agent and a silicone oil.

3. The composition according to claim 1 or 2, which further contains a matting agent.

10

4. The composition according to claim 1, wherein the amount of the fluorine-containing resin is 100 parts by weight, and the amount of the silicone oil is from 1 to 50 parts by weight based on 100 parts by weight of the fluorine-containing resin.

15

5. The composition according to claim 2, wherein the amount of the curable fluorine-containing resin is 100 parts by weight, the amount of the curing agent is from 0.1 to 5 equivalents per 1 equivalent of a curing reactive group in the curable fluorine-containing resin, and the amount of the silicone oil is from 1 to 50 parts by weight based on 100 parts by weight of the curable fluorine-containing resin.

20

6. A method of producing a coated leather, which comprises coating the leather paint composition according to claim 1, 2 or 3 on a leather.

25

7. A coated leather produced by the method according to claim 6.

8. The coated leather according to claim 7, wherein the leather is a natural leather, an artificial leather, a synthetic leather or a vinyl leather.

5 9. The coated leather according to claim 7 or 8, which is used for interiors of building constructions, interiors of vehicles, furniture items, shoes, bags, clothes and leather accessories.